


IN THE CLAIMS


1. (original): A composition comprising:

(a) a major dye component which is a mixture of copper phthalocyanine dyes of Formula (1):



wherein:

Pc represents a phthalocyanine nucleus of formula;



M is a cation;

x and y each independently have an average value of from 0.5 to 3.5;

(x+y) = 4; and

the sulfo and sulfonamide substituents are attached to a β-position on the phthalocyanine ring; and

(b) a liquid medium which comprises water and an organic solvent or an organic solvent free from water.

2. (original): A composition according to claim 1 wherein the copper phthalocyanine dyes of Formula (1) are prepared by cyclisation of 4-sulfo-phthalic acid to phthalocyanine  $\beta$ -tetrasulfonic acid in the presence of a nitrogen source, a copper salt and a base followed by chlorination and then amination.
3. (original): A composition according to either claim 1 or claim 2 where in the copper phthalocyanine dyes of Formula (1) x is 1 to 3.
4. (currently amended): A composition according to ~~any one of the preceding claims~~ claim 1 where in the copper phthalocyanine dyes of Formula (1) y is 1 to 3.
5. (currently amended): A composition according to ~~any one of the preceding claims~~ claim 1 where M is sodium, lithium, ammonia and volatile amines or mixtures thereof.
6. (currently amended): A composition according to ~~any one of the preceding claims~~ claim 1 which comprises:
  - (a) from 0.01 to 30 parts of dyes of Formula (1); and
  - (b) from 70 to 99.99 parts of a liquid medium which comprises a mixture of water and an organic solvent or an organic solvent free from water:wherein all parts are by weight.
7. (currently amended): A composition according to ~~any one of the preceding claims~~ claim 1 wherein at least 70% by weight of the total amount of phthalocyanine dye in said composition is of Formula (1).
8. (currently amended): A composition according to ~~any one of the preceding claims~~ claim 1 wherein at least 90% by weight of the total amount of phthalocyanine dye in said composition is of Formula (1).
9. (currently amended): A composition according to ~~any one of the preceding claims~~ claim 1 which is an ink suitable for use in an ink-jet printer.
10. (original): A process for forming an image on a substrate comprising applying an ink according to claim 9 thereto by means of an ink-jet printer.

11. (currently amended): A material printed with a composition according to ~~any one of claims 1 to 9 or by means of a process according to claim 10~~ claim 1.

12. (original): A material according to claim 11 that is a photograph printed using an ink-jet printer.

13. (original): An ink-jet printer cartridge comprising a chamber and an ink wherein the ink is in the chamber and the ink is as defined in claim 9.

14. (original): An ink-jet printer comprising a cartridge as defined in claim 13.

15. (new): A material printed with an ink-jet printer according to claim 10.